

Bondkrete SBR

Polymer bonding aid and mortar additive for concrete repair

Innovative products for your success

Uses

For improving the physical properties of cementitious mixes. Typical uses include, but are not limited to, the following:

- Bonding concrete repair mortars
- Floor toppings and screeds
- Waterproof renders and cementitious slurries
- Bonding agent for slip bricks, ceramic tiles, etc.

Advantages

- Single component liquid can be easily gauged as required
- Improves cohesion and workability
- Improves mortars to provide waterproof repairs, renders and toppings which are highly resistant to freeze/thaw cycling
- Improved tensile and flexural properties allow thin applications
- Excellent bond to concrete, masonry, stonework, plaster and block-board
- Contains no chloride admixtures

Standards compliance

Bondkrete SBR complies with the requirements of the United Kingdom Water Fittings Byelaws Scheme Tests of Effect on Water Quality.

Specification

Polymer bonding-aid and mortar additives: The polymer bonding aid and site-batched mortar shall be modified by the use of Bondkrete SBR, a single component styrene butadiene rubber emulsion.

Description

Bondkrete SBR is a modified **styrene butadiene rubber (SBR)** emulsion which is supplied as a ready to use white liquid. It is designed to improve the quality of site-batched cementitious mortars and slurries. Being resistant to hydrolysis, it is ideal for internal and external applications in conjunction with cement.

Properties

The results listed below were achieved by assessing the mechanical properties of a 3:1 sand:cement mortar containing Bondkrete SBR in the proportions 10 liters per 50 kg cement against a 3:1 sand:cement control mortar. The test methods used were in full accordance with BS 6319 at 28 days – air cured.

Substrate priming

The substrate should be thoroughly soaked with clean water and any excess removed prior to commencement. A slurry primer should be prepared consisting of 1 volume Bondkrete SBR to 1 volume clean water to 3 volumes fresh cement. To obtain a smooth consistency, the cement should be blended slowly into the premixed liquids. The slurry primer should be stirred frequently during use to offset settlement. The slurry primer should be scrubbed well into the surface of the substrate, being careful to avoid ponding. The repair mortar, topping or render must be applied on to the wet slurry primer. If the slurry primer dries before application of the mortar, it must be removed and the area should be re-primed before continuing.

Preparation of reinforcement (repairs only)

Expose fully any corroded steel in the repair area and remove all loose scale and corrosion deposits. Steel should be cleaned to a bright condition paying particular attention to the back of exposed steel bars. Grit-blasting is recommended for this process. Where corrosion has occurred due to the presence of chlorides, the steel should be high-pressure washed with clean water immediately after grit-blasting to remove corrosion products from pits and imperfections within its surface.

Reinforcing steel priming

Apply one full coat of I.O.Zinc 211 to any exposed steel reinforcement and allow to dry before continuing. If any doubt exists about having achieved an unbroken coating, a second application should be made and, again, allowed to dry before continuing.

Mix designs

A wide range of mix designs is achievable using Bondkrete SBR. Typical designs are detailed below:

1. Patching and repair mortar

(Recommended thickness: 6 mm to 40 mm)

50 kgs Ordinary Portland Cement
150 kgs grade C/M sharp sand
10 liters Bondkrete SBR
8 liters (approximately) clean water

2. Heavy-duty floor screed

(Recommended thickness: 10 mm to 40 mm)

50 kgs Ordinary Portland Cement
75 kgs 3 to 6 mm granite chips
75 kgs grade C/M sharp sand
10 liters Bondkrete SBR
6 liters (approximately) clean water

The screed should be of a semi-dry cohesive consistency.

Bondkrete SBR

Polymer bonding aid and mortar additive for concrete repair

Innovative products for your success

Test method	Typical result	Control	3. Render (Recommended thickness: 6mm to 9mm)
Compressive strength (BS 6319, Pt 2)	36 N/mm ²	27 N/mm ²	50 kgs Ordinary Portland Cement 150 kgs grade C/M sharp sand 10 liters Bondkrete SBR 6 liters (approximately) clean water
Tensile strength (ASTM C-190)	5.5 N/mm ²	2.7 N/mm ²	The render should be of a semi-dry cohesive consistency.
Flexural strength (BS 6319, Pt 3)	11.5 N/mm ²	7.9 N/mm ²	4. Bonding mortar for slip bricks, tiles, etc (Recommended thickness: 6 mm to 40 mm)
Slant shear bond (BS 6319, Pt 4)	37 N/mm ²	2.5 N/mm ²	50 kgs Ordinary Portland Cement 125 kgs grade C/M sharp sand 10 liters Bondkrete SBR 7 liters (approximately) clean water
Active solids content :	45% minimum		Water is adjusted to give a firm mortar. For fine joints, use grade M/F sand. Support where necessary until the mortar is set.
Chemical resistance :	Cementitious materials have limited chemical resistance.		Note: that these mix designs are based on the use of dry sand and aggregate. Adjustments must be made to the water demand relative to the moisture content of the sand and aggregate used. It should also be noted that, due to the frequent inconsistencies of site-stored materials and variable conditions, actual results may differ from those published above.

Note:

The addition of Bondkrete SBR to cement mortars reduces permeability and therefore helps reduce the rate of attack by aggressive chemicals, acid gases and water.

Design criteria

The application parameters for mortars modified by the use of Bondkrete SBR will differ depending on the actual mix design used, but should always be subject to a minimum applied thickness of 6 mm. Bondkrete SBR-modified mortars can generally be applied in sections of up to 40 mm thickness in horizontal locations and 15 mm in vertical locations, without the use of formwork. In overhead locations the thickness achievable without the use of formwork is largely dependent on the profile of the substrate.

Instructions for use

Preparation

Form the extremities of the application area to a depth of at least 10 mm to avoid feather-edging and to provide a square edge. Ensure a minimum depth of 6 mm is observed in the remaining area, up to the previously formed edge. Clean the surface and remove any dust, unsound or contaminated material, plaster, oil, paint, grease, corrosion deposits or algae. Oil and grease deposits should be removed by steam cleaning, detergent scrubbing or the use of a proprietary degreaser. Where breaking out is not required, roughen the surface and remove any laitance by light scrubbing or grit-blasting. The effectiveness of decontamination should then be assessed by a pull-off test.

Mixing

Care should be taken to ensure that Bondkrete SBR mortars are thoroughly mixed. A forced-action mixer is essential for large volume applications. Mixing in a suitably sized drum using an approved spiral paddle in a slow speed (400/500 rpm) heavy-duty drill is acceptable for minor areas. Weigh the cement, sand and, where required, aggregates into the mixer and dry blend together for one minute. With the machine in operation, add the pre-mixed Bondkrete SBR and clean water. Continue mixing for 3 minutes to ensure complete dispersal into the sand and cement. Make any small adjustment to the quantity of clean water but do not significantly exceed the literage of water shown above, additional water should be kept to a minimum. Continue mixing up to a maximum of 5 minutes until a smooth and fully homogeneous consistency is achieved with the required workability and application properties. It is critical that allowance is made for the moisture content of the sand and aggregate, particularly where stored on site.

Bondkrete SBR

Polymer bonding aid and mortar additive for concrete repair

Innovative products for your success

Application

For application to all surfaces, Bondkrete SBR mortars, toppings and renders must be well-compacted on to the primed substrate by trowel. It is frequently beneficial to work a thin layer of the mortar into the slurry primer and then build the mortar on to this layer. Exposed steel reinforcement should be completely encapsulated by the mortar. Bondkrete SBR mortars can be applied at a minimum thickness of 6 mm and up to 40 mm thickness, dependent on the location and configuration of the repair zone. Refer to the recommended thicknesses shown in the mix design section above. If the recommended thickness is exceeded and sagging occurs, the affected section must be completely removed and reapplied in accordance with the procedure described above. The use of formwork may facilitate achieving the required build. If formwork is used, it should have properly sealed faces to ensure that no water is absorbed from the repair material. Where thicker sections (up to a total thickness of 40 mm) are to be built up by hand or trowel application, the surface of the intermediate layers should be scratch-keyed and cured with Bondkrete AR. Application of the slurry primer and a further application of Bondkrete SBR mortar may proceed as soon as this layer has set.

Finishing

Bondkrete SBR mortars can be finished with a steel, plastic or wood float, or by a damp sponge technique, to achieve the desired surface texture. The completed surface should not be overworked.

Low temperature working

In cold conditions down to 5°C, the use of warm water (up to 30°C) is advisable to accelerate strength development. Normal precautions for winter working with cementitious materials should then be adopted.

High temperature working

At ambient temperatures above 35°C, the material should be stored in the shade and cool water used for mixing.

Curing

Bondkrete SBR mortars, toppings and renders are cement based. In common with all cementitious materials, they must be cured immediately after finishing in accordance with good concrete practice. The use of Bondkrete AR sprayed on to the surface of the finished mortar in a continuous film, is recommended. In harsh drying conditions, supplementary curing with polythene sheeting must be used. Over-coating with protective decorative finishes. Bondkrete SBR mortar repairs are extremely durable and will provide excellent protection to the embedded steel reinforcement within the repaired locations. The surrounding parts of the structure will generally benefit from the application of a barrier/decorative coating to limit the advance of chlorides and carbon dioxide, thus bringing them up to the same protective standard as the repair itself. Cemkrete recommend the use of the Coating range of protective, anti-carbonation coatings. These products provide a decorative and uniform appearance as well as protecting areas of the structure which might otherwise be at risk from the environment. Coating products may be applied over the repair area without prior removal of the curing membrane. Curing membrane must be removed prior to the application of coating products. This is best achieved by light grit or sand-blasting.

Cleaning

Bondkrete SBR should be removed from tools, equipment and mixers with clean water immediately after use. Cured material can only be removed mechanically. Equipment used with I.O.Zinc 211 should be cleaned using solvent.

Limitations

- Bondkrete SBR mortars, toppings and renders should not be applied when the temperature is below 5°C and falling.
- Bondkrete SBR mortars should not be exposed to moving water during application. Exposure to heavy rainfall prior to the final set may result in surface scour.
- If any doubts arise concerning temperature or substrate conditions, consult the local Cemkrete office.

Bondkrete SBR

Polymer bonding aid and mortar additive for concrete repair

Innovative products for your success

Estimating

Supply

Bondkrete SBR : 25 and 200 liter drums
I.O.Zinc 211 : 1 liter cans

Coverage

Bondkrete SBR : Refer to mix designs
Bondkrete SBR : Approx. 2 to 3 m²/litre
(as slurry primer)

Note: The actual usage of Bondkrete SBR will depend on the mix design used. The coverage figures for liquid products including the Bondkrete SBR slurry primer are theoretical - due to wastage factors and the variety and nature of possible substrates, practical coverage figures will be reduced.

Storage

Shelf life

All products have a shelf life of 12 months if kept in a dry store in the original, unopened bags or packs.

Storing conditions

Store in dry conditions in the original packs. If stored at high temperatures and/or high humidity conditions the shelf life may be reduced. Bondkrete SBR should be protected from frost.

Precautions

Health and safety

Cementitious mortars and slurries modified with Bondkrete SBR contain cement powders which, when mixed or become damp, release alkalis which can be harmful to the skin. During use, avoid inhalation of dust and contact with skin and eyes. Wear suitable protective clothing, gloves, eye protection and respiratory protective equipment. The use of barrier creams provides additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately - do not induce vomiting. I.O.Zinc 211, Bondkrete products, and solvent should not come in contact with the skin and eyes, or be swallowed. Ensure adequate ventilation and avoid inhalation of vapors. Some people are sensitive to resins, hardeners and solvents. Wear suitable protective clothing, gloves and eye protection. If working in confined areas, suitable respiratory protective equipment must be used. The use of barrier creams provides additional skin protection. In case of skin contacts with I.O.Zinc 211 remove immediately with resin removing cream followed by washing with soap and water. Do not use solvent. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately - do not induce vomiting.

Fire

Bondkrete SBR is non-flammable.

Additional Information

Cemkrete manufactures & supplies a wide range of those complementary products which includes:

- Waterproofing membranes & waterstops
- Joint sealants & filler boards
- Cementitious & epoxy grouts
- Specialized flooring materials
- Fireproof coating and systems
- Concrete admixture
- Repairing material

For further information on any of the above, please consult your local Cemkrete office - as below.

Important Note: Cemkrete warrants its materials free of manufacturing defects and produced as per standard specifications and sold under the terms and conditions of usages, whilst Cemkrete endeavors to ensure that any advice, recommendation, or information, given through its products literatures are reflects of the R&D in-house lab test and practical sites experience and knowledge based feed backs, however, the products are being used under various conditions and applied beyond its control where or how either directly or indirectly at various locations and places at a different stages that of an intended purposes and uses. Therefore, Cemkrete cannot hold warranty or responsible for resultant consequences, such as damages to the property or assets but the product itself.