



Dr. Fixit Pidiproof LW+

INTEGRAL LIQUID WATERPROOFING COMPOUND FOR CONCRETE & PLASTER

Description

Dr. Fixit Pidiproof LW+ is specially formulated integral liquid waterproofing compound composed of surface active plasticising agents, polymers & additives. It is used as an additive for cement concrete, mortar & plasters. It makes concrete cohesive and prevents segregation.

Standard Compliance / Specification

Meets the requirements of IS : 2645-2003 and IS: 9103-2000 standards

Areas of Application

Waterproofing of concrete and sand-cement mortars used in

- Basements,
- Roof slabs and screeds,
- Water tanks & water retaining structures,
- External plastering,
- Bathrooms and balconies,
- Sumps and drains

Features & Benefits

- **Corrosion resistant** - Makes concrete more cohesive, hence protects steel better against corrosion
- **Compatibility** - Being a liquid, easily dispersible & compatible with concrete/mortar mixes.
- **Permeability** - It reduces the permeability of water into concrete.
- **Strength** - The setting time and compressive strength of the concrete remains within the specification limits.
- **Shrinkage** - Reduces shrinkage crack development in plaster & concrete.
- **Workability** - Improves workability of freshly mixed cement concrete.
- **Durability** - Increases durability by improving waterproofing of concrete.

Method of Application

- Charge cement & aggregates to concrete mixer as per the mix design, mix in dry state for 1-2 minutes.
- Start addition of 75-80% mixing water & mix for 2-3 minutes.
- Dr. Fixit Pidiproof LW+ is added as per the recommended dosage into the remaining mixing / gauging water, then add to concrete mixer & mix for another 2 minutes.
- Place the concrete or apply plaster, as needed.
- Cure the applied mortar or concrete as per good construction practices.

Precautions & Limitations

- Do not add Dr. Fixit Pidiproof LW+ directly to dry cement & aggregate mix.
- Maintain water-cement ratio as low as possible.
- Do not increase the dosage of Dr. Fixit Pidiproof LW+ than the recommendation.



Technical Information

PROPERTIES	SPECIFICATION	RESULTS
Appearance		Free flowing liquid
Colour		Wine red
Sp. gr. @ 25°C		1.05 - 1.070
Non volatile content		13.5 - 14.5%
pH value		9- 13
Setting time, minutes	IS : 2645 : 2003	30 - 600 min.
Chloride content	IS : 2645 : 2003	Max. 2.00%
Water permeability	IS : 2645 : 2003	Passes
Compressive strength N /mm ²	IS : 2645 : 2003	As per the standard

Dosage

200 ml per 50 kg bag of cement

Packing

200 ml, 1, 5, 10, 20 & 100 litre

Shelf Life & Storage

- Best before 2 years from the date manufacture when in sealed pack and stored under proper condition.
- Store in a cool & dry place.

Health & Safety Precautions

- Use rubber hand gloves & safety goggles, while using Dr. Fixit Pidiproof LW+.
- In case of contact with skin, wash with plenty of water.
- Keep out of reach of children

Other Products Categories available

Dr. Fixit brings you the widest range of Construction Chemicals



Pidilite Industries Limited

Construction Chemicals Division
 Ramkrishna Mandir Road, Post Box No. 17411
 Andheri (E) Mumbai 400059 INDIA
 Tel +91-22-2835 7000 • Fax +91-22-2835 7008
 www.doctor-fixit.com • drfixitadvice@pilmail.com

Dr. Fixit Advice Centre (Toll Free No.) 1800-209-5504

DISCLAIMER The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and the on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.